

Technical Data Sheet

Ira-KNK Nano Graphene

Contact Information:

Manufacturer: Iranian Advanced Material Development

Address: Pishran tech Center, Tehran, Islamic Republic of Iran

Mobile: 98-9160201402

Tel: 98-2178991698

E-Mail: Info@iragraphene.ir

Website: www.iragraphene.com

1. Preparation Method

A proprietary ultra-high temperature processes enable the efficient production of graphene, delivering unique structural features and exceptional performance.

2. Characterization

Item	Value	Method-Standard
Appearance	Gray-Black Powder	Visual
Powder Size	1-10 μm	Particle size analyzer
Specific surface area	<10 m^2/g	BET N_2 adsorption method
Average layers	1-6	TEM-Raman
Carbon content	>97%	Elemental Analysis-ISO/609
ID/IG ratio of Raman	<0.2	Raman spectrometer-ISO/TS 21356-1
I2D/IG ratio of Raman	>0.6	Raman Spectrometer-ISO/TS 21356-1




Figure 1 - TEM Image of Ira-KNK Nano Graphene at 100nm level




Figure 2- TEM image of Ira-KNK Nano Graphene at 200nm level




Figure 3- Raman spectra of Ira-KNK